

AMENDMENTS TO THE SPECIFICATION

Please amend Chart 3A appearing on page 88 as follows:

Sample No.	NdFeB Coarse Magnet Powder (Co-less)										SmFeN Coarse Magnet Powder 10%Sm-7%Fe-13%N (at%)			Epoxy Resin Mixture Ratio (%)	
	Composition (at%)										Surfactant	Average Grain Diameter (μm)	Mixture Ratio		
	Nd	Dy	B	Fe	Ga	Nb	Zr	Co	La	Pr					
First Comparison Example	B1	12.5	-	6.4	Bal.	0.3	0.2	-	-	-	Yes	106	98	-	2
	B2	12.5	-	6.4	Bal.	0.3	0.2	-	-	-	Yes	106	98	-	2
	C1	12.7	-	6.2	Bal.	0.3	0.2	-	-	0.1	No	106	78	20	2
	C2	12.7	-	6.2	Bal.	0.3	0.2	-	-	0.1	Yes	106	78	20	2
	C3	12.7	-	6.2	Bal.	0.3	0.2	-	-	0.1	No	106	78	20	2
	D1	13.5	0.5	6.4	Bal.	0.3	0.2	-	-	-	Yes	45.35	78	20	2
	D2	13.5	0.5	6.4	Bal.	0.3	0.2	-	-	-	Yes	425	78	20	2
	E1	12.5	-	6.4	Bal.	0.3	0.2	-	-	-	Yes	106	45	53	2
E2	12.5	-	6.4	Bal.	0.3	0.2	-	-	-	Yes	106	88	10	2	
F1	12.5	-	6.4	Bal.	0.3	0.2	-	-	-	Yes	106	79.5	20	0.5	
F2	12.5	-	6.4	Bal.	0.3	0.2	-	-	-	Yes	106	73	15	12	